



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 20, 2015

Ms. Erisbet Soto
HEALTH CARE INTERIORS
1000 W Crosby Rd, Ste 100
Carrollton, TX 75006

Reference: Laboratory Test Report
Lab Identification No. 16381
Invoice No. 47180 (Attached)

Dear Ms. Soto:

One (1) fabric sample, identified as **RUS P**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	4.0	22.83
2	0.0	28.64
3	0.0	23.53
4	0.0	15.86
5	0.0	25.95
6	0.0	21.51
7	0.0	19.23
8	0.0	23.65
9	0.0	23.15
10	4.0	21.89
AVG.	0.8	22.63

The fabric sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment