



**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

→ "We Test Per Your Request" ←

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
[www.diversifiedtestinglabs.com](http://www.diversifiedtestinglabs.com)

November 7, 2024

Ms. Windy Sherwin  
VALDESE WEAVERS  
P.O. Box 70  
Valdese, NC 28690

Reference: Laboratory Test Report  
Lab Identification No. 62067  
Invoice No. 93400

Dear Ms. Sherwin:

One (1) fabric sample, identified as **F-0269175-01 SO# 15463931-10**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". The results are as follows:

**Test Results**

<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	6.39
2	0.0	16.99
3	0.0	10.87
4	0.0	7.03
5	0.0	14.21
6	0.0	6.79
7	0.0	12.11
8	0.0	7.10
9	0.0	11.11
<u>10</u>	<u>0.0</u>	<u>18.56</u>
<b>AVG</b>	<b>0.0</b>	<b>11.12</b>

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

